

PRATIK

It is a cement-based plastering material that can be applied to interior and exterior surfaces by hand or machine.

■ ADVANTAGES

- Provides quick and easy application by hand and machine.
- It has high adhesion to the surface it is applied to. It does not cause sagging or shedding.
- Since it spreads easily, a homogeneous finish is achieved on the applied surface.
- It has high pressure resistance.
- It is resistant to external climatic conditions.

■ SCOPE OF APPLICATION

- It is applied on all cement-based surfaces and facades consisting of all mesh elements such as brick, aerated concrete and pumice stone.

■ WARNINGS AND RECOMMENDATIONS

- It is not applied on metal surfaces.
- Foreign materials should never be added.
- The application surface should be cleaned of dust and dirt before application.
- Application should be avoided in humid, rainy, windy and high temperature weather conditions.
- It should not be applied on surfaces that are frozen, melting or in danger of rain or frost within 24 hours.
- It should not be applied directly on surfaces such as wood, wood and metal.
- It should be protected from frost, sun and strong wind for the first 24 hours after application.
- Application is recommended between + 5 °C - + 35 °C.

■ STORAGE

Packaging	25 kg Kraft Bag
Colour	Grey
Shelf Life	1 year from date of manufacture when stored unopened and undamaged in a dry, moisture-free environment. Packages should be kept tightly closed when not in use.

■ CONSUMPTION

14-16 kg/m² - 1 cm

■ APPLICATION FEATURES

- DryFiX PRATIK plaster material should be slowly added into 4.50-5.00 liters of clean water and mixed with the help of a mixer until a homogeneous mixture is obtained.
- The prepared mixture is left to rest for 5-10 minutes depending on weather conditions; It is ready for use by mixing again for 1-2 minutes.
- In machine applications, water is adjusted to the appropriate water ratio and sprayed on the surface.

All technical information stated in this product data sheet is based on laboratory tests.
Actual values may vary due to circumstances beyond our control.

İZERSAN YAPI MALZ.SAN VE TİC.LTD.ŞTİ.

Center Factory: Egemenlik Mah. 6016/6 Sk. No:19/1 Işıkent Bornova/ İZMİR

www.dryfix.com.tr - info@izersan.com.tr

Tel&Fax: +90 850 777 05 35



PRATIK

■ TECHNICAL SPECIFICATIONS AND PERFORMANCE VALUES

Product Structure	Cement- based powder
Colour	Grey
Water Mixing Ratio	4,50-5,00 L water / 25 kg
Reference Standard	TS EN 1504-3 / Class R4
Bond Strength	$\geq 0,2 \text{ N/mm}^2$
Compressive Strength	$\text{CS IV} \geq 6 \text{ N/mm}^2$
Mass per Unit Volume of Hardened Mortar	$1.500 \text{ kg/m}^3 (\pm 200)$
Water Vapor Permeability (μ)	≤ 25
Average Thermal Conductivity, W/m.K ($\lambda_{10, \text{dry}}$)	$\leq 0,80$
Capillary Water Absorption and Water Permeability	W1; C $\leq 0,40 \text{ kg/(m}^2 \cdot \text{min} 0,5)$

The stated times apply for 20°C substrate and ambient temperature; increase at lower temperatures and decrease at higher temperatures. DryFiX is not responsible for the application errors arising from use of product beyond its intended purpose of failure to comply with the forgoing application conditions and advice on the product.

■ SAFETY PRECAUTIONS

During use and storage, appropriate work clothes, glasses, gloves and masks should be used for worker health and safety. Eye, mouth and skin contact should be avoided. The contacted area should be washed with plenty of water. In more dangerous situations or if the product is swallowed, a specialist doctor should be consulted immediately. Food and drink should not be allowed into application areas. It should be kept out of reach of children. For detailed information, the Safety Data Sheet (SDS) should be consulted.

■ LEGAL WARNING

Applications that may occur if the product is used for purposes other than its intended purpose or if the above-mentioned conditions are not complied with: from the mistakes of İzersan Yapı Malz. San. VE TİC. LTD. ŞTİ. is not responsible.

All technical information stated in this product data sheet is based on laboratory tests. Actual values may vary due to circumstances beyond our control.

İZERSAN YAPI MALZ.SAN VE TİC.LTD.ŞTİ.

Center Factory: Egemenlik Mah. 6016/6 Sk. No:19/1 Işıkkent Bornova/ İZMİR

www.dryfix.com.tr - info@izersan.com.tr

Tel&Fax: +90 850 777 05 35

